# DESCRIPTION

Causeway Kenlux Anti-Corrosive paint is an alkyd based synthetic paint for protection against corrosion for all types of metal surfaces. It is ideal to be used as a primer before application of Enamel paint.

- Good Adhesion.
- Anti-rust Properties.
- Excellent base for Subsequent Coatings.

# **TYPICAL USES**

- Act as a primer or anti-corrosive coating for ferrous metals.
- Also recommended as undercoat for wood.

### APPLICATION

- Method of application
- Conventional Spray
  - Brush
  - Airless Spray

# **APPLICATION INSTRUCTIONS**

- Ensure that the substrate is free of rust, oil, grease and other contaminants prior to any painting work.
- Dilute the paint to the required viscosity, depending on the type of application method employed.

### **HEALTH & SAFETY**

Always keep paint out of reach of children. Ensure good ventilation during application and drying. Do not smoke while painting. Highly flammable. Store in a cool dry place away from heat and sparks.



# TECHNICAL DATA SHEET KENLUX ANTI CORROSIVE PAINT

# TECHNICAL DATA

o COLOR	: Red, Grey, Brown, Green & Black
• COMPONENTS	: Single
○ FINISH	: Semi-gloss
○ CURING MECHANISM	: Oxidation process
○ VISCOSITY	: 150 sec (Ford 4)
○ SPECIFIC GRAVITY	: ~ 1.30 +/- 0.10
• VOLUME OF SOLIDS	: Approx 55%
○ THINNER	: Causeway Turpentine Causeway Thinner
O MIXING RATIO	: 25% (Brush) / 40% (Spray)
○ SPRAY VISCOSITY	: 15 sec (Ford 4)
<ul> <li>RECOMMENDED THICKNESS PER COAT</li> </ul>	: 25-35µm
<ul> <li>THEORETICAL</li> <li>COVERAGE</li> </ul>	: ~ 10-12m²/L (Based on 25-30μm DFT)
<ul> <li>DRYING TIME</li> </ul>	: 45 minutes (Touch dry) 16 hours (Hard dry)
<ul> <li>RE-COATING</li> <li>INTERVAL</li> </ul>	: 08 hours
○ POT LIFE	: N/A
O SHELF LIFE	: Best before 24 months
<mark>PACKING</mark> o 200 ml o 500 ml	o 1 Litre o 4 Litres

Rev: 01

#### Issue Date: 24/10/2016

The Technical Data is provided only as general advice. However, since service and applications conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on these data. The above information may vary from time to time and we reserve the right to modify the data without prior notice.