

DESCRIPTION

Sunny 2K PU Wood Sealer is a high performance two component polyurethane sealer for furniture wood coatings. It possess excellent filling and sanding properties, which will result in a smooth sealed even surface for the subsequent coat. Sunny 2K PU Wood Sealer will preserve the wood while showing the natural wood grain appearance.

- High Solid
- Rapid Drying
- Excellent Filling

TYPICAL USES

- Ideally suited for most types of premium furniture, including kitchen benches, cupboards, tables and similar.
- Also suitable for doors, windows, frames & etc.
- Also recommended to be applied on wooden floors for long lasting durable finish.

APPLICATION

- Use conventional spray methods or airless spray method.

SURFACE PREPERATION

- Sand down the bare wood up to 180P sand paper. Fill the larger dents with Causeway AQLAC wood Putty. (If required)
- Old varnished areas should be stripped well back then treated as new wood.

APPLICATION INSTRUCTIONS

- Add 2 parts of 2K PU Wood Sealer to 1 part of 2K PU Wood Hardener and mix thoroughly. Addition of Causeway 171 Uni Thinner (PU thinner) depends on the application method.
- Apply the mixture by brush, spray. Allow to dry for 2 hours and sand down with 320P sand paper and dust off.
- Apply the 2nd coat of 2K PU Wood sealer by brush or spray. Allow to dry for 2 hours and sand down with 320P sand paper and dust off.
- Finish Up with desired coating system.
- Use the mixture within the given pot life.

HEALTH & SAFETY

Always keep paint out of reach of children. Ensure good ventilation during application and drying. Do not smoke while painting. Highly flammable. Store in a cool dry place away from heat and sparks.



TECHNICAL DATA SHEET

SUNNY 2K PU WOOD SEALER PREMIUM **(BASE COAT)**

TECHNICAL DATA

- COLOR : Clear
- COMPONENTS : Two
- FINISH : Satin
- CURING MECHANISM : Reaction with the Hardener
- VISCOSITY : 10 poise
- SPECIFIC GRAVITY : 1.100+/-0.200gcm⁻³
- VOLUME OF SOLIDS : ~45-50%
- THINNER : Causeway PU Thinner (50%)
- MIXING RATIO : Sealer : Hardener = 2:1
- SPRAY VISCOSITY : 18 seconds (Ford 4)
- RECOMMENDED THICKNESS PER COAT : 30um (DFT)
- THEORETICAL COVERAGE : 12m²/L (25µm : DFT)
- DRYING TIME : 15Minutes (Touch dry)
2 Hours (Sanding)
- RE-COATING INTERVAL : 2 Hours
- POT LIFE : 1 hours (@ 30°C)
- SHELF LIFE : best before 24 months

PACKING

- 1Litre + 500 ml (W24 Hardener)
- 4 Litre + 1L (Hardener)+ 1L (W24 Hardener)