

## **DESCRIPTION**

Causeway Water Based Exterior Sealer is designed to penetrate into the exterior substrate and improves adhesion of the emulsion paints top coats and roofing paints. Can be used interior and exterior.

## **TYPICAL USES**

Causeway exterior Sealer can be applied on all types of exterior cement plasters, exterior ceiling's, asbestos sheets, concrete etc. as an undercoat. Specially recommended for powdery surfaces.

## **SURFACE PREPARATION**

Ensure that the surface to be painted is free from any loose paint, dust or grease. Any previous growth of fungus, algae or moss needs to be removed. Before application of the sealer minor surface imperfections such as holes, dents and cracks are to filled using mixture of cement and fine sand (in the ratio 1:3) or suitable exterior type of putty. Freshly plastered surface must be allowed to cure completely. Must be dry and pH of the surface must be neutral at the time of application of sealer.

## **DILUTION**

Can be mixed with up to 10 % water.

## **APPLICATION**

Preferably applied by brush to penetrate in to substrate. Recommended to top coat with suitable exterior paints once dry without delay. One coat is sufficient. Highly absorbent surface 2 coats are recommended.

## **DRYING TIME**

Surface drying time 15-20minutes. Recoating time 4-6 hours at 25°C and 50% Relative Humidity.

## **Health and Safety:**

This is Lead safe product. Keep out of reach of children. Ensure good ventilation during application and drying. In case of skin contact wash with soap and water. Avoid contact with eyes. In case of contact, rinse eyes with plenty of water and seek medical advice. Harmful if swallowed. Do not induce vomiting. Immediately seek medical advice.

Total Lead below 90ppm. Conforms to Consumer Authority Direction No.36.



## **TECHNICAL DATA SHEET** **CAUSEWAY EXTERIOR SEALER**

### **TECHNICAL DATA**

○ COLOR	: colourless
○ COMPONENTS	: Single
○ FINISH	: Semi-Gloss
○ CURING MECHANISM	: Air drying
○ VISCOSITY	: 4 P
○ SPECIFIC GRAVITY	: 1.103 g/ml
○ VOLUME OF SOLID	: 50%
○ VOC Content	: Not Detected
○ RECOMMENDED THICKNESS PER COAT	: N/A
○ THEORETICAL COVERAGE	: 12m <sup>2</sup> - 15 m <sup>2</sup> / Ltr
○ No. OF COATS	: 1-2 coats depends on condition of the surface
○ RE-COATING INTERVAL	: Min 4-6 hours at 30°C
○ POT LIFE	: N/A
○ SHELF LIFE	: Best before 24 months

### **PACKING**

- 1 Litre
- 4 Litres